

PRODUCT DATA SHEET

Avery Dennison® 5300 Blockout Films

Issued: 01/2023

Introduction

Avery Dennison® 5300 Blockout Films are premium quality cast films that are especially designed for graphics involving internally illuminated light box applications. Avery Dennison® 5300 Blockout Films are designed to provide complete light blocking characteristics. Avery Dennison® 5301 Blockout Film exhibits a uniformly lustre white finish and is uniformly black on the adhesive side. Avery Dennison® 5303 Blockout Film has a black lustre finish and is uniformly white on the adhesive side.

Conversion

Avery Dennison® 5300 Blockout Films offer excellent conversion using computerised sign cutting, hand cutting and die cutting.

Recommendations

- » Graphics for internally illuminated signs and canopies on both rigid and flexible substrates
- » Avery Dennison® 5300 Blockout Films are generally applied as second surface substrate in combination with Avery Dennison® 4500TF and Avery Dennison® 5500QM Translucent Films

Custom colours: Colormatching service is offered, however some limitations apply.

Features

- » Total light block control, less than 0,001% light transmission
- » Lustre finish on face of the film, matching with other Avery Dennison® backlit sign products
- » Provides a very good and stable layflatness during handling and conversion
- » Offers the choice of a white or a black face film
- » Excellent adhesion to a wide variety of substrates
- » Superior dimensional stability
- » Excellent performance as second surface media
- » Excellent performance for flat and slightly curved designs



Face Film

100 micron premium, cast vinyl film



Adhesive

permanent, clear, acrylic based



Backing

polycoated kraft paper, 135 g/m²



Durability

5 years



Shelf Life

2 years

Physical Characteristics

Features	Test method ¹	Results
Product		
Caliper, facefilm (micron)	ISO 534	100 micron
Caliper, facefilm + adhesive (micron)	ISO 534	125 micron
Light Transmission (%)		<0.001 %
Dimensional stability (mm max.)	FINAT FTM 14	0.4 mm max.
Shelf life (years)	Stored at 22° C/50-55 % RH	2 years
Durability ² (years)	Vertical exposure	5 years
Flammability		self-extinguish
Accelerated ageing	SAE J 1960, 1500h exposure	No negative impact
Adhesive		
Elongation (%)	DIN 53455	100% min
Adhesion, initial (N/m)	FINAT FTM-1, glass	500 N/m
	PMMA	450 N/m
	Polycarbonate	375 N/m
	Ultralon IV	400 N/m
	FINAT FTM-1, glass	580 N/m
	PMMA	550 N/m
	Polycarbonate	560 N/m
	Ultralon IV	400 N/m
Adhesion, after 24 hours (N/m)		
	FINAT FTM-1, glass	580 N/m
	PMMA	550 N/m
	Polycarbonate	560 N/m
	Ultralon IV	400 N/m
Temperature range		
Application temperature (Minimum: °C)		Minimum: +10° C
Service temperature (°C to +°C)		-40° to +80° C
Chemical properties³		
Chemical resistance	Mild acids	No effect
Solvent resistance	Mild alkalis and salts	No effect
Solvent resistance	Applied to aluminium	No effect exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel.

Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

2) Durability: The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.

3) Prolonged immersion in gasoline and similar fluids is not recommended.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.

Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

© 2023 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.