

PRODUCT DATA SHEET

Avery Dennison® Interior Reflective Solar Films

Issued: 02/2019

Revision: 4

Introduction

The **R Silver** films provide maximum energy efficiency and value. By rejecting excess solar radiation, R Silver films cut heat build-up through the glazing.

Description

Color: Silver

Technology: Metallization by sputtering

Face:

R Silver 20 i
R Silver 35 i
R Silver 50 i

Adhesive: Pressure sensitive **Permanent** – Solvent based acrylic

Liner: PET

Warranted Durability¹: 12 years

Fire Certification: B-s1, d0 (DIN EN 13501-1)

Features:

- **Excellent solar heat and glare rejection**
- **Upgraded building appearance**
- **Daytime privacy**
- **99+% UV block**

Common Applications:

R Silver films are the most popular choice for commercial projects with their strong visual statement, effective heat rejection, and the quickest return on investment.

Optical & Solar Properties:

	R Silver 20 i		R Silver 35 i		R Silver 50 i	
	Single Pane	Double Pane	Single Pane	Double Pane	Single Pane	Double Pane
Visible Light Transmitted %	18	17	33	31	51	46
Visible Light Reflected (Int) %	62	62	41	42	23	25
Visible Light Reflected (Ext) %	61	61	42	44	24	29
U V Block %	99	99	99	99	97	98
Total Solar Energy Reflected %	55	49	39	37	24	25
Total Solar Energy Transmitted %	13	12	25	22	39	34
Total Solar Energy Absorbed %	32	38	36	41	37	41
Shading Coefficient	0,25	0,35	0,40	0,49	0,58	0,63
Total Solar Energy Rejected %	78	70	65	58	50	45
Solar Heat Gain Coefficient	0,22	0,30	0,35	0,42	0,50	0,55
Emissivity (Room side)	0,71	0,71	0,72	0,72	0,81	0,81
U-Value Winter	0,97	0,46	0,98	0,46	1,02	0,47
K-Value Winter	5,51	2,62	5,57	2,63	5,78	2,70
Glare Reduction %	80	79	63	62	44	43
Luminous Efficacy	0,72	0,49	0,86	0,64	0,87	0,73

Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change without notice.

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

1) Warranted Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased. With regard to Avery Dennison Architectural Window Film Products, the durability shall no differ between the climatic zones, but the same durability shall apply to all climatic zones.