
Product Data Sheet

2M CL PET/ R0302N3/ 3M PET ESD-WH

Product code : MZ1006B2

Issue date: 2014-07-23

Facestock:

2M CL PET ESD is surface treated polyester film, featuring excellent tear strength, dimensional stability, chemical resistance and clarity. Specific testing is required.

Caliper: 50 mic. (±10%) ISO 534
Basis Weight: 75 g/m² (±10%) ISO 536

Adhesive:

R0302N3 is industrial grade ultra removable acrylic adhesive, featuring good clarity, excellent wet-out performance and excellent heat stability over broad range of temperature in removability without adhesive stain on a broad range of substrates over long period of time.

Min. appl. temp.: ↑ 5°C
Service temp.: -20°C ~ +180°C
Peel Adhesion ↓ 2g/in FTM #2
Thickness 8mic (±10%) ISO 534

Liner:

3M PET ESD-WH is a 75mic siliconised clear polyester film liner with anti-static white coating treated featuring good dimensional stability for stable release as well as excellent die cutting performance.

Caliper: 75 mic (±10%) ISO 534
Basis Weight: 105 g/m² (±10%) ISO 536

Applications and use:

This product is suitable for use in a wide range of protective film application specifically designed for glass work-in-process application.

RoHS & Halogen Free

Printing/Converting:

This product can be die-cut and stripped at high speeds on standard web-fed presses.

Shelf life:

1 year when stored at 22°C at 50% RH

Statement of Practical Use:

As with all pressure sensitive materials, this product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.

Avery Dennison Roll Materials Korea



Seoul Tel: +82 2 3406 6200 Fax: +82 2 3406 6210	Daegu Tel: +82 53 581 8645 Fax: +82 53 581 8647	Busan Tel: +82 51 262 9001 Fax: +82 51 262 9013	Anyang Tel: +82 31 361 0240 Fax: +82 31 454 8481
--	--	--	---

Warranty

Information concerning Products are based upon tests believed to be reliable but do not represent a guarantee or warranty. Products are provided on the basis that any Purchaser has independently determined the suitability of the Products and Purchaser's purposes. The Company warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year of delivery (but not afterwards), upon notification thereof within seven (7) days of such appearance and substantiation that the Products have been stored and applied in accordance with the Company standards, the Company shall within a reasonable period correct such defects by providing a suitable replacement without charge at the Company's plant or at the location of the Products (at the Company's election) provided however, if the Company in its sole discretion determines that replacement is not commercially practical, the Company may issue a credit in favour of the Purchaser in an amount not to exceed the purchase price actually paid for the Products. Any implied warranty of merchantability fitness for particular purpose or other warranty of quality, whether express or implied by law, is hereby excluded to the extent permitted by law. In no event shall the Company be liable for any incidental, indirect or consequential damages including, but not limited to, loss of profit, loss of use or loss of capital. The remedies of the Purchaser set forth herein are exclusive, and the total potential liability of the Company arising out of any contract of or from the manufacture, sale, delivery, resale, installation or use of any products shall not exceed the purchase price of the products upon which liability is based.