

Fasson® 60# Cast Gloss/C2075/40#SCK

Spec# 17715

Facestock:

Fasson® 60# Cast Gloss is a cast-coated gloss paper featuring high strength and excellent ink receptivity. Offers excellent printing with Water and UV Flexo, Screen, Offset and certain UV Letterpress ink systems.

Basis Weight:	60# per ream +/- 10% (500 sheets 25" X 38"
Caliper:	0.0039 inches +/- 10%
Tensile:	MD 32# per inch width CD 15# per inch width
Tear:	MD 42 grams per sheet CD 54 grams per sheet
Stiffness:	MD 200 mg CD 80 mg

Adhesive:

Fasson® C2075 is a freezer grade permanent adhesive designed to combine optimum cold-temperature performance with good diecutting and stripping characteristics. The adhesive is compatible with a variety of facestocks.

FDA Compliance: Title 21, Section 175.105 of the Code of Federal Regulations (21 CFR 175.105). Compliance to this regulation permits the use of this adhesive in applications for which the adhesive either (1) is separated from the food by a functional barrier, which will prevent the migration of any of the adhesive components to the food, or (2) has incidental contact with food limited to the trace amount at the seams or the edges of the label.

Type:	Hot Melt Rubber
Minimum Application Temperature:	0° F
Service Temperature Range:	-65° F to +160° F

Typical Performance Data: 60# Semigloss

Stainless Steel

Loop Tack:	2.6 lbs.
Peel Adhesion:	1.4-1.6 lbs.

Treated HDPE

Loop Tack:	1.8 lbs.
Peel Adhesion:	1.0-1.2 lbs.

Polypropylene

Loop Tack:	2.4 lbs.
Peel Adhesion:	1.7-1.9 lbs.

Recycled Corrugated

Loop Tack:	0.4 lbs.
Peel Adhesion:	0.4-0.5 lbs.

Glass

Loop Tack:	2.6 lbs.
Peel Adhesion:	1.4-1.6 lbs.

Liner:

40#SCK is a bleached super-calendered kraft stock featuring high internal strength, toughness, and tear resistance. Used primarily for roll-to-roll label applications.

Basis Weight:	42# per ream \pm 10% (24" X 36" 500 sheets)
Caliper:	0.0025 inches \pm 10%
Tensile:	MD 38# per inch width CD 20# per inch width
Tear:	MD 36 grams CD 41 grams

Total Construction Caliper (approximate): 0.0072 inches \pm 10%

Shelf Life

Unless specified otherwise in this document, one year when stored at 72°F at 50% RH

Statement of Practical Use

All pressure-sensitive materials should be tested thoroughly under end-use conditions to ensure they meet the requirements of the specific application.

Warranty

All sales and contracts for sale are expressly conditioned on the buyer's assent to Avery Dennison's terms and conditions found on its website at www.na.fasson.com. Avery Dennison hereby objects to any term, different from or additional to Avery Dennison's terms, contained in any buyer communication in any form, unless agreed to in a writing signed by an officer of Avery Dennison.

www.na.fasson.com

Label and Packaging Materials-North America

8080 Norton Parkway
Mentor, OH 44060
800-944-8511

